



FLUOROPON®

CERTIFIED LABORATORY
TEST REPORT

CHEMICAL SPOT TESTING

ACID RESISTANCE

TEST PROCEDURES:

CHEMICAL SPOT TEST PER ASTM D 1308,
COVERED SPOT TEST PROCEDURE 7.2

PRODUCT TESTED:

VALSPAR FLUOROPON COATING

TESTS RESULTS:

- 10% HYDROCHLORIC ACID SOLUTION
 - 24 HOUR TEST, NO VISIBLE CHANGES
- 20% HYDROCHLORIC ACID SOLUTION
 - 18 HOUR TEST- NO BLEACHING
- 20% SULFURIC ACID
 - 18 HOUR TEST- NO BLEACHING
- 25% SODIUM HYDROXIDE
 - 1 HOUR TEST- NO COLOR CHANGE, NO BLISTERING
- 20% MURIATIC ACID
 - 15 MINUTE TEST- NO COLOR CHANGE, NO BLISTERING

SAMPLE NUMBER:

431A886

LOCATION:

THE VALSPAR CORPORATION
FT. MYERS, FL

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.