



FLUROPON®

CERTIFIED LABORATORY
TEST REPORT

CYCLIC SALT FOG/UV EXPOSURE

SALT SPRAY

TEST PROCEDURES:	3000 HOURS PER ASTM D 5894 INCLUDING SCRIBE REQUIREMENT
PRODUCT TESTED:	VALSPAR FLUROPON COATING ON GALVALUME® SUBSTRATE
TESTS RESULTS:	ACCEPTABLE
SCRIBE:	TEST RATING OF 8, 1/32 INCH (1 MM) CREEPAGE FROM SCRIBE PER ASTM D 1654, PROCEDURE A
FIELD:	TEST RATING OF 10, NO BLISTERING PER ASTM D 1654 PROCEDURE B (REF. ASTM D 714)
SAMPLE NUMBER:	433B173
LOCATION:	THE VALSPAR CORPORATION FT. MYERS, FL

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.