



FLUROPON®

CERTIFIED LABORATORY
TEST REPORT

SALT SPRAY

SALT SPRAY

TEST PROCEDURES:	SALT SPRAY- 2000 HOURS PER ASTM B 117, INCLUDING SCRIBE REQUIREMENT
PRODUCT TESTED:	VALSPAR FLUROPON COATING ON GALVALUME® SUBSTRATE
TESTS RESULTS:	ACCEPTABLE
SCRIBE:	TEST RATING OF 7, 4MM CREEPAGE FROM SCRIBE PER ASTM D 1654, PROCEDURE A
FIELD:	TEST RATING OF 8, PER ASTM D 1654 PROCEDURE B (REF. ASTM D 714)
SAMPLE NUMBER:	433X515
LOCATION:	THE VALSPAR CORPORATION FT. MYERS, FL

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.