



FLUOROPON®

CERTIFIED LABORATORY
TEST REPORT

SALT SPRAY

SALT SPRAY

TEST PROCEDURES:	SALT SPRAY - 3000 HOURS PER ASTM B 117, INCLUDING SCRIBE REQUIREMENT
PRODUCT TESTED:	VALSPAR FLUOROPON COATING ON ALUMINUM SUBSTRATE
TESTS RESULTS:	ACCEPTABLE
SCRIBE:	TEST RATING OF 7, 1/16 (2MM) CREEPAGE FROM SCRIBE PER ASTM D 1654, PROCEDURE A
FIELD:	TEST RATING OF 10, PER ASTM D 1654 PROCEDURE B (REF. ASTM D 714)
SAMPLE NUMBER:	433X515
LOCATION:	THE VALSPAR CORPORATION FT. MYERS, FL

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.